



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number: **0 336 406 B1**

(12)

EUROPEAN PATENT SPECIFICATION

- (45) Date of publication of patent specification: **06.10.93** (51) Int. Cl.⁵: **A61L 25/00, A61L 31/00, C08F 299/06, A61B 19/08**
- (21) Application number: **89106025.3**
- (22) Date of filing: **06.04.89**

(54) **Ultraviolet cured peelable film and method therefor.**

- (30) Priority: **08.04.88 US 179354**
- (43) Date of publication of application:
11.10.89 Bulletin 89/41
- (45) Publication of the grant of the patent:
06.10.93 Bulletin 93/40
- (84) Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI LU NL SE
- (56) References cited:
EP-A- 0 184 233
DE-A- 3 437 531
FR-A- 2 284 622
US-A- 4 542 012

- (73) Proprietor: **Becton Dickinson and Company**
One Becton Drive
Franklin Lakes New Jersey 07417-1880(US)
- (72) Inventor: **Lee, Min-Shiu**
9642 Meadow Woods Lane
Spring Valley Ohio 45370(US)
Inventor: **Gleason, John**
2295 Infirmary Road
Dayton Ohio 45418(US)
Inventor: **Taller, Robert A.**
7150 Wilderness Way
Centerville Ohio 45459(US)
- (74) Representative: **von Kreisler, Alek,**
Dipl.-Chem. et al
Patentanwälte
Von Kreisler-Selting-Werner,
Postfach 10 22 41,
Bahnhofsvorplatz 1
D-50462 Köln (DE)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description**BACKGROUND OF THE INVENTION**

1. Field of the Invention. This invention relates to films, and more specifically, relates to a film forming liquid which is ultraviolet curable to an in situ formed surgical drape or wound dressing.

2. Background of the Invention. Conventional surgical drapes and wound dressings are composed of preformed films which may be solid but are generally porous. Such films are conventionally referred to as continuous and are usually adhered to the skin by a suitable adhesive. Several disadvantages result from this procedure. For example, preformed drapes often do not form a tight continuous seal with the skin so that avenues are available for bacterial penetration. Further, preferred films are difficult to adhere over irregular anatomical contours such as hands and knees. Care must be taken that nothing other than the drape (as, for example, a sleeve of a surgical gown) comes in contact with the adhesive prior to emplacement of the drape.

Surgical drapes which are applied as a solution in an appropriate solvent and subsequently cured by evaporation of the solvent are known. Cardarelli et al., in U.S. Patent No.4,374,126 discloses an antimicrobial film of a polyacrylic acid crosslinked with urea prepared by casting a solvent solution of the ingredients and evaporating the solvent. Good antimicrobial effect, transpiration, skin adherence and resistance to body fluids while being removable with soap and water are described.

U.S. Patent No.4,542,012 to Dell discloses an antimicrobial composition applied to the skin as a solvent solution which forms a film upon solvent evaporation. The composition includes an isocyanate-terminated polyurethane prepolymer linked to an isocyanate-terminated copolymer of an acrylate and N-vinylpyrrolidone by a chain extender. Iodine complexed with the polyvinylpyrrolidone is included as an antiseptic.

Burleigh, in U.S. Patent No. 4,613,544 discloses a sheet material consisting of a backbone polymeric membrane matrix having transmembrane passageways which are filled with a hydrophilic polyoxyalkylene polyurethane applied as a prepolymer and cured in situ by heat or light.

Ultraviolet curing of acrylate terminated polyurethanes is disclosed by Szycher et al. in U.S. Patent No. 4,483,759.

Several of the disadvantages of adhesively adhered preformed drapes have been addressed by these inventions, but deficiencies remain. The solvents used for casting may be irritative to the skin, and may require a long time for evaporation. In particular, solvent evaporation in a medical environment such as an operating room may be both a health hazard and a fire hazard. It is toward the overcoming of these deficiencies that this invention is directed.

SUMMARY OF THE INVENTION

A radiation cured film is formed of a copolymer of a vinyl monomer and a prepolymer of a polyurethane oligomer and oxyalkyl acrylate terminal groups. Preferred vinyl monomers are acrylates and vinyl lactams. The oligomer may be formed of a polyisocyanate, preferably a diisocyanate, a polyol, preferably a polyesterpolyol, and a chain extending diol. The most preferred prepolymer is the reaction product of isophorone diisocyanate, polycaprolactone and 1,4-butanediol. The most preferred vinyl monomer is N-vinyl pyrrolidone.

In another aspect of the invention, a method to form a peelable film includes casting a mixture of the vinyl monomer, the prepolymer and a photoinitiator onto a surface to form a liquid film and curing the liquid film by exposure to electromagnetic radiation, preferably ultraviolet (UV) light. In the present disclosure, the term peelable is understood to mean that the film is removable in one piece with substantially no tearing or fragmentation, and the terms casting and curing respectively mean forming a liquid film on a surface and causing the liquid film to polymerize and solidify.

The cured film of the invention is ideal for use as an in situ cured liquid drape or wound dressing and overcomes problems associated with prior art, preformed wound dressings. The present invention is applied to a patient's skin as a liquid and then cured to form a film. Thus, it flows freely into all depressions of the skin so that, when cured, no channels remain to provide access routes for bacteria. This skin-tight film is achieved without the use of a toxic or flammable solvent which must be removed as required in prior art films. Because the films of the invention are formed without solvent and are removable in one piece by simple peeling, cleanliness in a medical environment is enhanced. Curing of the film of the invention may be carried out in a matter of seconds with a hand held ultraviolet lamp, a major advantage in an operating room where solvent evaporation is time consuming and a health hazard.

DETAILED DESCRIPTION OF THE INVENTION

While this invention is satisfied by embodiments in many different forms, there will herein be described in detail preferred embodiments of the invention, with the understanding that the present disclosure is to be considered as exemplary of the principles of the invention and is not intended to limit the invention to the embodiments described. The scope of the invention will be measured by the appended claims and their equivalents.

The present invention provides a continuous film prepared by curing a layer of a liquid formulation with ultraviolet light. The cured film has a balance of tensile strength, modulus, elongation and slit tear strength which makes it ideal as a surgical drape or wound dressing which adheres firmly to the skin but which is easily removed by peeling.

In this disclosure, the following abbreviations are used.

PCL - polycaprolactone

PTMEG - polytetramethylene ether glycol

15 PPEG - polypropylene ether glycol

BDO - 1,4-butanediol

IPDI - isophorone diisocyanate

HEA - hydroxyethyl acrylate

HEMA - hydroxyethyl methacrylate

20 IDA - isodecyl acrylate

2-EHA - 2-ethylhexyl acrylate

THFMA - tetrahydrofurfuryl methacrylate

NVP - N-vinyl pyrrolidone

DMF - dimethylformamide

25 MEK - methyl ethyl ketone

The liquid formulation of the invention is a mixture of a vinyl monomer and a prepolymer having a polyurethane oligomer and oxyalkyl acrylate terminal groups. The polyurethane oligomer may be formed from a polyisocyanate, a polyol and a chain extending diol. Preferred polyisocyanates are aromatic, aliphatic or alicyclic diisocyanates, such as diphenylmethane-4,4'-diisocyanate, diphenylmethane-3,3'-diisocyanate, IPDI, dicyclohexylmethane-4,4'-diisocyanate, and hexamethylene diisocyanate. The most preferred diisocyanate is IPDI.

The polyol component may be a polyether glycol such as polyethylene oxide, PPEG and PTMEG. Preferred polyols are polyester glycols, such as polyethylene adipate and PCL. Particularly preferred polyester glycols have a molecular weight from about 500 to 5000. The most preferred polyol is PCL of molecular weight about 2000.

The chain extender may be a low molecular weight branched or unbranched diol of up to 10 carbon atoms or mixtures thereof. Representative nonlimiting examples of chain extenders are BDO; ethylene glycol; diethylene glycol; triethylene glycol; 1,2-propanediol; 1,3-propanediol; 1,6-hexanediol; 1,4-bis(hydroxymethyl) cyclohexane, and hydroquinone dihydroxyethyl ether. Preferred chain extenders are 1,6-hexanediol and BDO.

Reaction of the diisocyanate, polyol and diol to give the oligomer may be carried out by heating the reactants for a suitable time, either neat or preferably in a suitable solvent, such as MEK. A conventional catalyst, such as dibutyl tin dilaurate, may be used to accelerate the reaction. The ratio of the reagents may be chosen such that the oligomer is capped with isocyanate groups. Thus, any ratio may be used which has about one equivalent more diisocyanate than the combined equivalents of polyol and diol. For example a suitable oligomer may be formed from 6 equivalents of diisocyanate reacted with about 0.5 to 3 equivalents of polyol and about 4.5 to 2 equivalents of diol. Most preferably, the oligomer contains about 1.0 to 1.2 equivalents of polyol and 4.0 to 3.8 equivalents of diol. An example of a typical procedure for oligomer synthesis is given in Example I, however, various modifications of this procedure set forth therein are well-known to those skilled in the art.

A prepolymer having oxyalkyl acrylate terminal groups may be prepared by reacting the isocyanate caps of the oligomer and a suitable hydroxylated acrylate. Suitable hydroxylated acrylates are, for example, hydroxyethyl, hydroxypropyl and hydroxybutyl acrylates and methacrylates, although it is evident that a wide variety of other hydroxylated acrylate derivatives may be used. Referred hydroxylated acrylates for oxyalkyl capping of the prepolymer are HEA and HEMA.

Reaction of the hydroxylated acrylate and the isocyanate caps on the oligomer may conveniently be carried out merely by adding the acrylate to the solvent solution of the oligomer and heating for a suitable period. If desired, recovery of the prepolymer from the solvent may be carried out by any conventional

technique, as for example, by solvent evaporation or by dilution with a solvent to precipitate the prepolymer, followed by filtration and drying. Preferably, the prepolymer in the solvent is merely diluted with the vinyl monomer, as described below.

In some cases, it may be desirable to crosslink the prepolymer. A crosslinking agent may be added to the mixture of diisocyanate, polyol and diol in order to crosslink the oligomer to any desired level. Alternatively, the crosslinking agent may be mixed with the hydroxylated acrylate. Any conventional crosslinking agent as known in the art of polyurethane synthesis may be used. Particularly suitable crosslinking agents are triols, as for example, trimethylol propane. The quantity of crosslinking agent may be from 0 to about 10 weight percent of the polyol. It is understood that when the crosslinking agent is part of the oligomer, the total equivalents of polyol, diol and triol crosslinking agent is one less than the equivalents of diisocyanate.

Although a film of the prepolymer may itself be cast and cured to give a peelable film of the invention, it is preferred to form a mixture of the prepolymer and a vinyl monomer prior to casting. The vinyl monomer serves to reduce the viscosity of the prepolymer for convenience in casting, and becomes part of the polymer matrix of the film upon curing.

A wide variety of vinyl monomers of mixtures thereof may be mixed with the prepolymer, as, for example, IDA, HEA, THFMA, HEMA, 2-EHA, vinyl acetate, 1,4-butanediol diacrylate, trimethylolpropane triacrylate, 2-phenylethyl methacrylate, and the like. Preferred vinyl monomers are lactams substituted on the nitrogen atom with an olefinic group, such as a vinyl or isopropenyl group. The lactam may have 4, 5 or 6 carbon atoms and thus, for example, may be a pyrrolidone, piperidone, piperazinedione or caprolactam.

The preferred vinyl monomer is NVP, neat or mixed with one or more additional vinyl monomers, as IDA, 2-EHA or HEA. The weight percentage of vinyl monomers in the mixture to be cast and cured may be about 1 to 50%, preferably about 25-40%.

A photoinitiator may be added to the mixture to catalyze the copolymerization of the acrylate terminated prepolymer and the vinyl monomer. Any conventional photoinitiator as known in the art may be used. Examples of suitable photoinitiators are given in Szycher et al., supra, and selection of a suitable photoinitiator is well within the purview of one skilled in the art. Particularly useful photoinitiators are the Irgacure™ cyclohexyl phenyl ketone derivatives (Ciba Geigy).

An antimicrobial agent may also be added to the mixture prior to casting and curing. Any antimicrobial agent which is substantially stable to ultraviolet light and which may be released slowly from the cured film may be used. Exemplary of suitable antimicrobial agent are povidone iodine, chlorohexidene or chlorohexideneiodine complex. The quantity of antimicrobial agent to be added may be from about 1 to 10, preferably 2 to 6 weight percent.

In order to obtain the desired film properties, conventional additives such as flow aids, flattening agents, plasticizers, polymerization inhibitors, heat stabilizers and surface cure modifiers may sometimes be added to the formulation prior to casting and curing. A suitable surface cure modifier, for example is TMPTMP, trimethylol propane tri-(3-mercaptopropionate).

Casting is a conventional operation, and in the present disclosure may be performed by dipping, spraying, spreading or any other suitable means. Preferably, the mixture is cast neat onto a suitable surface, as, for example, silicon release paper or a glass plate. In the most preferred embodiment of the invention, the mixture is cast onto the skin of an animal, for example, over a wound or surgical incision site of a human being. The cast liquid films may be adjusted to any desired thickness by conventional means, as a doctor knife, and may be from about 0.1 to 2.5mm, preferably about 10 μ to 1.0 mm thick.

Curing may be carried out merely by exposing the cast liquid film to electromagnetic radiation, preferably UV light. A conventional UV lamp may be used, as, for example, a Conrad-Hanovia Model 45080 (Conrad-Hanovia Inc., Newark, NJ) or a Blak-Ray Model UVL-56 (Ultraviolet Products, Inc., San Gabriel, CA). Surface cure occurs almost instantaneously. The length of exposure required to bulk cure the liquid film depends on the thickness of the film. In general, films of from about 25 μ to 1.0 mm in thickness are bulk cured in about 15 to 120 sec. when the lamp is positioned about 15 cm. from the film. Parameters of curing such as lamp intensity, duration of exposure and distance of the film from the lamp are well understood by those skilled in the art and no further details are needed.

The cured films of the invention may be evaluated for their tensile strength, modulus, elongation and tear strength by ASTM methods well known in the art. The testing results below are given in pounds per square inch (psi) and pounds per linear inch (pli), which are equivalent to 0.07 kg/cm² and 0.178 kg/cm respectively. Tensile strength is a measure of the force, generally given in psi, required to break a polymer. Elongation is a measure of the ability of a polymer to stretch without breakage, and is generally reported as a percentage of an initial value. The term modulus defines the force (in psi) required to stretch a polymer to a given percentage of elongation. Tensile, modulus and elongation may be measured by ASTM procedure

D 638 using an Instron Universal Testing instrument, Model 1122. Slit tear strength is the force (in pli) required to propagate a tear in a film along the line of a previously introduced slit, and may be tested by ASTM procedure, D 1938. Die C tear is the force (in pli) required to initiate a tear at a previously introduced notch, and may be tested by ASTM procedure D 1004.

5 It has been found that tear strength is an important property for determining whether a film is suitable for use as a peelable drape or wound dressing. In general, a slit tear strength of about 5-50 pli combined with a die C tear strength of about 45-250 pli confers peelability to the cured film of the invention. Preferred films have slit tear and die C tear strengths of about 20-45 and 100-200 pli respectively. Broad ranges of tensile, and elongation which, when combined with the tear strengths given above, define peelable films of
10 the invention may be 1,000-10,000 psi and 150%-400% respectively. Modulus is a less important parameter, and may be from 10-1,000 psi at 5% elongation.

Representative nonlimiting examples of peelable films of the invention are given in Table I. The films were prepared as described in Example I from the indicated commercial polyol, IPDI, BDO and HEA in the equivalent ratio 1:6:4:1.

TABLE I

POLYOL	Tensile psi	Modulus psi @ 5%	Elongation %	Tear Strength, pli.	
				Slit	Die C
PTMEG ^a	2800	880	280	10	190
PPEG ^b	1500	465	215	11	120
(linear polyester) ^c	2100	730	280	24	200
PCL ^d	2000	505	320	46	160

a TeracolTM 2000 ... E.I. Du Pont de Nemours and Co. Wilmington, DE

b NIAXTM PPG 2025 ... Union Carbide, Tarrytown, NY

c RucoTM S-1059-55 ... Ruco Polymer Corp., Hicksville, NY

d TONETM 0240 ... Union Carbide, Danbury, CT

For comparison purposes, cured films were prepared from various commercially available acrylate capped polyurethane prepolymers copolymerized with NVP by the procedure of Example I. The composition and properties of these films are given in Table II.

TABLE II																
COMPOSITION (a)	COMPOSITION, WEIGHT PERCENT															
	A ^b	B	C	D	E	F	G	H	I	J	K	L	M	N		
UVITHANE 782 TM	100	100	70	70	70	70	60	60	60	70	70	70	50	40		
CHEMPOL TM 19-4833	-	-	-	-	15	-	10	5	15	15	10	-	-	5		
PHOTOMER 4770 TM	-	-	-	-	-	15	10	5	15	15	-	10	-	5		
AMICON LV-2321-S9 TM	-	-	-	-	-	-	-	-	-	-	-	-	20	20		
HVP	-	-	30	30	15	15	20	30	10	-	20	20	30	30		
DEAP ^a	2	-	2	-	-	-	-	-	-	-	-	-	-	-		
IRGACURE 651 TM	-	2	-	2	2	2	2	2	2	2	2	2	2	2		
PROPERTIES																
TENSILE psi	2400	2200	310	400	1700	1600	2700	500	1000	620	3100	2800	2500	1900		
MODULUS 55 psi	24	23	30	32	59	28	65	29	50	23	55	31	70	120		
ELONGATION %	175	190	100	120	115	110	110	110	83	100	150	145	127	107		
TEAR (511t) pli	6	0	0	0	0	0	3	0	0	0	1	3	3	6		
TEAR (Die C) pli	130	78	16	8	50	26	32	30	26	17	50	120	50	49		
a - acetophenone based photoinitiator - Union Carbide																
b - Although this formulation has physical properties which would make it peelable, its viscosity was too high for effective casting.																

It is seen that these films exhibit adequate tensile strength and elongation, but tear strength is very low. In general, these compositions do not lead to peelable films.

In order to simulate actual use conditions, liquid films may be cast onto pig skin and cured as given in Example II and their physical properties and peelability from the pig skin determined. Table III gives data for three films prepared from IPDI, HEA, BDO, IrgacureTM 184 and the indicated polyols and vinyl monomers. The films of Table III are all peelable.

TABLE III

	Composition	Tensile psi	Modulus psi @5t	Elongation %	Tear Strength, pli	
					Slit	Die C
1	TONETH 0305, 0.25 eq. TONETH 0240, 0.75 eq. 2-HEA, 25.2 wt. % NVP, 14.0 wt. %	1568	33	233	7	67
2	NIAX TM PPC 2025 1.0 eq. IDA, 9.8 wt. % NVP 26.4 wt. %	1034	180	225	17	93
3	TONETH 0240, 1.0 eq. IDA, 9.8 wt. % THFMA, 4.9 wt. % NVP 25.0 wt. %	2298	390	285	34	159

Likewise, in live animal testing of various cured films of the invention in accordance with Example III, the films of Table III are peelable.

EXAMPLE I

General Procedure for Synthesis of Cured Films

A mixture of IPDI (6 equivalents), BDO (4 equivalents), 2,000 molecular weight polyol (1 equivalent), and 0.05% stannous octoate in MEK at 90% solids was heated and stirred at 70 °C until oligomer formation was 98-105% complete. The mixture was cooled to 50 °C and 1 equivalent of HEA was added. The mixture was stirred until the percent of free isocyanate was 0.5 or less to give a prepolymer having oxyalkyl acrylate terminal groups. If necessary to maintain a workable viscosity some of the reactive diluent described below, may be added during a prepolymer formation.

The prepolymer was combined with 2 weight percent of IrgacureTM, and sufficient NVP, optionally containing one or more other vinyl monomers, to give a total solid content of about 60%. Up to 10 weight percent of a reactive diluent, such as IDA, may be added to reduce viscosity. The mixture was stirred until all components were homogeneously dispersed, set aside to allow all bubbles to escape and cast onto silicone release paper. The thickness of the film was adjusted to 50 μ with a doctor knife and cured by exposure to the Conrad-Hanovia lamp until a tackless surface was obtained, generally about 1 second. The cured film was removed from the release paper for evaluation of physical and mechanical properties.

EXAMPLE II

General Procedure for Curing Onto Pig Skin

A belly section of pig skin was cleaned and degreased by wiping several times with cotton balls saturated with acetone and finally with alcohol. Cured films were formed on the pig skin by the procedure of Example I and allowed to remain on the skin in ordinary light for several hours to determine whether oil blooming to the surface of the skin would cause the films to release from the skin. Data obtained for representative films is given in Table III.

EXAMPLE III

Live Animal Testing of Peelability

A 40-45 pound pig was anaesthetized, and a belly section was washed and shaved with electric clippers. Liquid films, prepared in accordance with Example I, were adjusted to a thickness of about 0.6 mm and were cured in situ with the Blak-Ray UVL 56 (2 minutes exposure) and Blak-Ray B-100A (1 minute

exposure) lamps. The cured films had tensile strengths of 2500-2700 Psi, elongation of 230-330%, slit tear strengths of 16-44 pli and Die C tear strengths of 70-170 pli. All films easily peeled from the pig skin intact.

Claims

5

1. A peelable film comprising an ultraviolet-cured copolymer of at least a vinyl lactam and a prepolymer, said prepolymer comprising a polyurethane oligomer from the reaction of a diisocyanate, a polyol and chain extending diol, said oligomer having an oxyalkyl acrylate terminal group, said film having a slit tear strength of 5-50 pounds per linear inch and a die C tear strength of 45-250 pounds per linear inch.

10

2. The film of Claim 1 wherein said copolymer further comprises a copolymerized second vinyl monomer.

3. The film of Claim 1 wherein said prepolymer further comprises a crosslinking agent.

15

4. The peelable film according to claim 1 comprising an electromagnetic radiation-cured copolymer of a vinyl monomer and a prepolymer, said prepolymer comprising a polyurethane oligomer having an oxyalkyl acrylate terminal group.

20

5. The peelable film according to claim 1 comprising an ultraviolet-cured copolymer of at least N-vinyl pyrrolidone and a prepolymer, said prepolymer comprising a polyurethane oligomer from a reaction of an alicyclic diisocyanate, a polyesterdiol and a chain extending diol of no more than ten carbon atoms, said oligomer having an oxyalkyl acrylate terminal group, said film having a slit tear strength of 5-50 pounds per linear inch and a die C tear strength of 45-250 pounds per linear inch.

25

6. A method for forming a peelable film according to claim 1 on a surface comprising:

preparing a mixture comprising a photoinitiator, an olefinically substituted lactam and a prepolymer, said prepolymer including a polyurethane oligomer from the reaction of a diisocyanate, a polyol and a chain extending diol, said oligomer having an oxyalkyl acrylate terminal group;

casting said mixture onto a surface to form a liquid film; and

30

exposing said liquid film to ultraviolet light whereby said vinyl lactam and said prepolymer copolymerize to form a peelable film on said surface.

7. A method for forming a peelable film according to claim 1 on a surface comprising:

preparing a mixture comprising a photoinitiator, a vinyl monomer and a prepolymer, said prepolymer including a polyurethane oligomer having an oxyalkyl acrylate terminal group;

35

casting said mixture onto a surface to form a liquid film; and

exposing said liquid film to electromagnetic radiation whereby said vinyl monomer and said prepolymer copolymerize to form a peelable film on said surface.

40

8. A method for forming a peelable film according to claim 1 on a surface comprising:

preparing a mixture comprising a photoinitiator, N-vinyl pyrrolidone and a prepolymer, said prepolymer including a polyurethane oligomer from a reaction of a diisocyanate, a polyester diol and a chain extending diol of no more than ten carbon atoms, said oligomer having an oxyalkyl acrylate terminal group;

45

casting said mixture onto a surface to form a liquid film; and

exposing said liquid film to ultraviolet light whereby said N-vinyl pyrrolidone and said prepolymer copolymerize to form a peelable film on said surface.

Patentansprüche

50

1. Abziehbare Folie, umfassend ein ultraviolett-ausgehärtetes Copolymer aus wenigstens einem Vinyl-lactam und einem Prepolymer, wobei das Prepolymer ein Polyurethan-Oligomer aus der Reaktion eines Diisocyanats, eines Polyols und eines kettenverlängernden Diols ist, wobei das Oligomer eine endständige Oxyalkylacrylat-Gruppe hat, worin die Folie eine Schlitz-Reißfestigkeit von 5 bis 50 lbs./linear inch und eine Die C-Reißfestigkeit von 45 bis 250 lbs./linear inch hat.

55

2. Folie nach Anspruch 1, worin das Copolymer weiterhin ein copolymerisiertes zweites Vinyl-Monomer umfaßt.

3. Folie nach Anspruch 1, worin das Copolymer weiterhin ein Vernetzungsmittel umfaßt.
4. Abziehbare Folie nach Anspruch 1, umfassend ein durch elektromagnetische Strahlung ausgehärtetes Copolymer aus einem Vinyl-Monomer und einem Prepolymer, wobei das Prepolymer ein Polyurethan-Oligomer mit einer endständigen Oxyalkylacrylat-Gruppe umfaßt.
5. Abziehbare Folie nach Anspruch 1, umfassend ein ultra-violett-ausgehärtetes Copolymer aus wenigstens einem N-Vinylpyrrolidon und einem Prepolymer, wobei das Prepolymer ein Polyurethan-Oligomer aus der Reaktion eines alicyclischen Diisocyanats, eines Polyesterdiols und eines kettenverlängernden Diols mit nicht mehr als 10 Kohlenstoff-Atomen umfaßt, wobei das Oligomer eine endständige Oxyalkylacrylat-Gruppe hat, worin die Folie eine Schlitz-Reißfestigkeit von 5 bis 50 lbs./linear inch und eine Die C-Reißfestigkeit von 45 bis 250 lbs./linear inch hat.
6. Verfahren zur Bildung einer abziehbaren Folie nach Anspruch 1 auf einer Oberfläche, umfassend die Herstellung eines einen Photoinitiator, ein olefinisch substituiertes Lactam und ein Prepolymer umfassenden Gemischs, wobei das Prepolymer ein Polyurethan-Oligomer aus der Reaktion eines Diisocyanats, eines Polyols und eines kettenverlängernden Diols umfaßt, wobei das Oligomer eine endständige Oxyalkylacrylat-Gruppe hat;
das Gießen des Gemischs auf eine Oberfläche, um einen flüssigen Film zu bilden; und
das Einwirkenlassen von ultraviolettem Licht auf den flüssigen Film, wodurch das Vinylactam und das Prepolymer unter Bildung einer abziehbaren Folie auf der Oberfläche copolymerisieren.
7. Verfahren zur Bildung einer abziehbaren Folie nach Anspruch 1 auf einer Oberfläche, umfassend die Herstellung eines einen Photoinitiator, ein Vinyl-Monomer und ein Prepolymer umfassenden Gemischs, wobei das Prepolymer ein Polyurethan-Oligomer mit einer endständigen Oxyalkylacrylat-Gruppe umfaßt;
das Gießen des Gemischs auf eine Oberfläche, um einen flüssigen Film zu bilden; und
das Einwirkenlassen von elektromagnetischer Strahlung auf den flüssigen Film, wodurch das Vinyl-Monomer und das Prepolymer unter Bildung einer abziehbaren Folie auf der Oberfläche copolymerisieren.
8. Verfahren zur Bildung einer abziehbaren Folie nach Anspruch 1 auf einer Oberfläche, umfassend die Herstellung eines einen Photoinitiator, N-Vinylpyrrolidon und ein Prepolymer enthaltenden Gemischs, wobei das Prepolymer ein Polyurethan-Oligomer aus der Reaktion eines Diisocyanats, eines Polyesterdiols und eines kettenverlängernden Diols mit nicht mehr als 10 Kohlenstoff-Atomen umfaßt, wobei das Oligomer eine endständige Oxyalkylacrylat-Gruppe hat;
das Gießen des Gemischs auf eine Oberfläche, um einen flüssigen Film zu bilden; und
das Einwirkenlassen von ultraviolettem Licht auf den flüssigen Film, wodurch das N-Vinylpyrrolidon und das Prepolymer unter Bildung einer abziehbaren Folie auf der Oberfläche copolymerisieren.

Revendications

1. Pellicule détachable comprenant un copolymère durci par la lumière ultra-violette d'au moins une lactame vinylique et un prépolymère, ledit prépolymère comprenant un oligomère de polyuréthane provenant de la réaction d'un diisocyanate, d'un polyol et d'un diol à chaîne étendue, ledit oligomère possédant un groupe terminal acrylate d'oxyalkyle, ladite pellicule possédant une résistance à la propagation du déchirement de 89,3 à 893 kg par mètre linéaire (5 à 50 livres par pouce linéaire) et une résistance à la déchirure en matrice en forme de C de 804 à 4465 kg par mètre linéaire (45 à 250 livres par pouce linéaire).
2. Pellicule selon la revendication 1, dans laquelle ledit copolymère comprend de plus un second monomère vinylique copolymérisé.
3. Pellicule selon la revendication 1, dans laquelle ledit prépolymère comprend de plus un agent de réticulation.
4. Pellicule détachable selon la revendication 1, comprenant un copolymère durci par un rayonnement électromagnétique d'un monomère vinylique et d'un prépolymère, ledit prépolymère comprenant un

oligomère de polyuréthane possédant un groupe terminal acrylate d'oxyalkyle.

5. Pellicule détachable selon la revendication 1, comprenant un copolymère durci par la lumière ultra-violette d'au moins une N-vinylpyrrolidone et un prépolymère, ledit prépolymère comprenant un oligomère de polyuréthane provenant d'une réaction d'un diisocyanate alicyclique, d'un poly(ester de diol) et d'un diol à chaîne étendue ne dépassant pas dix atomes de carbone, ledit oligomère possédant un groupe terminal acrylate d'oxyalkyle, ladite pellicule possédant une résistance à la propagation de la déchirure de 89,3 à 893 kg par mètre linéaire (5 à 50 livres par pouce linéaire) et une résistance à la déchirure en matrice en forme de C de 804 à 4465 kg par mètre linéaire (45 à 250 livres par pouce linéaire).
6. Procédé pour former une pellicule détachable selon la revendication 1 sur une surface comprenant les opérations consistant:
 - à préparer un mélange comprenant un photo-amorceur, une lactame substituée oléfiniquement et un oligomère provenant de la réaction d'un diisocyanate, d'un polyol et d'un diol à chaîne étendue, ledit oligomère possédant un groupe terminal acrylate d'oxyalkyle;
 - à couler ledit mélange sur une surface pour former une pellicule liquide; et
 - à exposer ladite pellicule liquide à la lumière ultraviolette, ainsi ladite lactame vinylique et ledit prépolymère copolymérisent pour former une pellicule détachable sur ladite surface.
7. Procédé pour former une pellicule détachable selon la revendication 1 sur une surface comprenant les opérations consistant:
 - à préparer un mélange comprenant un photo-amorceur, un monomère vinylique et un prépolymère, ledit prépolymère comprenant un oligomère de polyuréthane possédant un groupe terminal acrylate d'oxyalkyle;
 - à couler ledit mélange sur une surface pour former une pellicule liquide; et
 - à exposer ladite pellicule liquide à un rayonnement électromagnétique, ainsi ledit monomère vinylique et ledit prépolymère copolymérisent pour former une pellicule détachable sur ladite surface.
8. Procédé pour former une pellicule détachable selon la revendication 1 sur une surface comprenant les opérations consistant:
 - à préparer un mélange comprenant un photo-amorceur, une N-vinylpyrrolidone et un prépolymère, ledit prépolymère comprenant un oligomère de polyuréthane provenant d'une réaction d'un diisocyanate, d'un poly(ester de diol) et d'un diol à chaîne étendue ne dépassant pas dix atomes de carbone, ledit oligomère possédant un groupe terminal acrylate d'oxyalkyle;
 - à couler ledit mélange sur une surface pour former une pellicule liquide; et
 - à exposer ladite pellicule liquide à la lumière ultra-violette, ainsi ladite N-vinylpyrrolidone et ledit prépolymère copolymérisent pour former une pellicule détachable sur ladite surface.